

Polyolefin Heat-Shrink Tubing

FITCOTUBE[®] FT-SNME

Medium wall, flexible tube with high shrink ratio and hot melt adhesive coating. Electrical insulation, pressure-proof sheating, anti-corrosion and moisture protection in all areas of energy supply, telecommunication technology as well as piping construction.

Operating temperature:	- 40°C to + 120°C
Shrink temperature:	+ 125°C
Shrink ratio:	4:1
Standard colors:	Black



Description	Inner Diameter (mm)		Wall Thickness (mm)
	as supplied (min.)	after full recovery (max.)	after full recovery (nom.)
FT-SNME-8/2	8	2	1.70
FT-SNME-12/3	12	3	2.20
FT-SNME-22/6	22	6	2.60
FT-SNME-34/7	34	7	2.60
FT-SNME-40/12	40	12	2.60
FT-SNME-56/16	56	16	2.70
FT-SNME-63/19	63	19	2.80
FT-SNME-75/22	75	22	3.00
FT-SNME-95/26	95	26	3.20
FT-SNME-120/36	120	34	3.30
FT-SNME-140/42	140	42	3.50
FT-SNME-160/50	160	50	3.50

Packaging:

1-meter-lengths. Cut or printed lenghts on request.

Processing note:

Care for clean and accurate cutting edge. Start shrinkage on the end. Pre-heat metal body. For a shrinking size of $\geq 28/6$ we recommend using a propane burner (approx. 30-50 mm diameter and soft flame).

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · <u>www.gremco.de</u> • Version: 1809

FITCO^{*} = trademark of GREMCO All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.



Polyolefin Heat-Shrink Tubing

FITCOTUBE[®] FT-SNME

Attributes	Testing	Value		
Mechanical				
Ultimate Elongation	IEC 60684-2	350 %		
Tensile Strength	IEC 60684-2	13 MPa		
Longitudinal Change	IEC 60684-2	≤ 10 %		
Thermical				
Fire behavior	IEC 60684-2 method C	not self-extinguishing		
Low Temperature Flexibility	IEC 60684-2	- 40 °C		
Long-term ageing (150°C x 168h) Ultimate Elongation Tensile Strength	IEC 60684-2 IEC 60684-2	250 % 12 MPa		
Electrical				
Dielectric Strength	IEC 60684-2	25 kV/mm		

Chemical

Volume Resistivity

Corrosion	IEC 60684-2	no corrosion
Fungus- and rot-restistance	IEC 60684-2	rate 1

 $10^{14} \,\Omega/cm$

IEC 60684-2

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · <u>www.gremco.de</u> • Version: 1809

FITCO^{*} = trademark of GREMCO All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.