

Braided Hose

FITCOFLEX® -I-PET12

Self-extinguishing braid with high extension ratio made of polyester.

Application:

Bundling and protection of industry cabling and sets of test cabling. All-purpose application for a high number of different diameter ranges because of its high expansion ratio.

Operating temperature: -55°C to +150°C

Standard color: Black



Bestellbezeichnung	Field of application (mm)	
	(∅ min)	(∅ max)
FITCOFLEX®-I-PET12 3	2	7
FITCOFLEX®-I-PET12 5	3	8
FITCOFLEX®-I-PET12 6	4	8
FITCOFLEX®-I-PET12 8	6	10
FITCOFLEX®-I-PET12 10	8	14
FITCOFLEX®-I-PET12 12	10	14
FITCOFLEX®-I-PET12 13	12	15
FITCOFLEX®-I-PET12 14	12	16
FITCOFLEX®-I-PET12 16	14	22
FITCOFLEX®-I-PET12 20	12	25
FITCOFLEX®-I-PET12 22	20	35
FITCOFLEX®-I-PET12 24	22	35
FITCOFLEX®-I-PET12 26	24	40
FITCOFLEX®-I-PET12 30	28	40
FITCOFLEX®-I-PET12 40	38	50
FITCOFLEX®-I-PET12 50	48	55

Special sizes on request

Key Benefits:

- Monofilament: ∅ 0,22mm made of polyester
- Melting point 250°C - 260°C
- Self-extinguishing (DIN75200 / FMVSS 302)
- Fire class (DIN5510 part 1+2)
- High expansion & 100% recyclable
- UL94-V2 & very good media resistance

Braided Hose

FITCOFLEX[®]-I-PET12

Packaging: On spools, cut lengths or printed tubing on request.

Properties	Test Method	Typical Value
Mechanical		
Abrasion resistance	LV 312-3 (ISO 6722) PSA 9645870999E GME 8618	≥ 5,000 cycles (class E) ≥ 7,000 cycles (class 4) 144,000 strokes
Shrinkage performance	ISO 6722	≤ 4%
Impact resistance	PSA D421245 LV 312-3	No damage (C/200/50/-30°C) No damage (700/1200g bei -40°C)
Thermal		
Long term aging (3.000h x 150°C)	LV312-2	Pass
Short term aging (240h x 175°C)	LV312-2	Pass
Hot water jet test	LV312-3	Pass (No cracks or damage)
Flammability	FMVSS 302 (DIN 75200) DIN 5510-2 Fire test UL94 V	Self-extinguishing (Category B) Flammability class S4 Smoke emission SR2 Dripability class ST2 Classification: V2
Smoke index	NF F 16-101 NF F 16-102/STM-S-001 DIN EN 45545-2 (NF X 70-100)	F2 Pass (Requirement R22 & R23 -> Hazard Level HL3)
Smoke density	DIN EN 45545-2 (EN ISO 4589-2)	Pass (Requirement R22 & R23 -> Hazard Level HL3)
Hydrolysis resistance	GME 00053	Pass
Chemical		
Oxygen index	NF F 16-101 NF F 16-102/STM-S-001 DIN EN 45545-2 (EN ISO 5659-2)	I2 (Requirement R22 & R23 -> Hazard Level HL3)
Fogging	VW 50180	Pass (≤ 2mg)
Emission	VW 50180	Pass (≤ 50µg C/G)