

PTFE heat shrink tubing with melting FEP core

FITCOTUBE® TF/FP-B

Dual Wall, high temperature resistant heat shrinkable tubing made of PTFE with melting FEP core for sealing and encapsulation of components with highest demands on temperature resistance and/or chemical resistance.

Operating temperature: -190°C to +205°C
Shrinking temperature: Ca. 330°C
Shrink ratio: 1.5 : 1
Standard color: Nature / transparent (milky)



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after full recovery (max.)	after full recovery (nom.)
TF/FP-036B-S	0.91	0.00	N.V.
TF/FP-060B-S	1.52	0.00	N.V.
TF/FP-130B-S	3.30	0.00	N.V.
TF/FP-160B-S	4.05	0.00	N.V.
TF/FP-190B-S	4.80	1.60	0.90
TF/FP-250B-S	6.40	3.20	0.90
TF/FP-350B-S	8.90	4.80	0.90
TF/FP-450B-S	11.40	7.90	1.40
TF/FP-700B-S	17.80	11.20	1.40
TF/FP-950B-S	24.10	16.00	1.65
-thin walled-			
TF/FP-065B-L	1.65	0.00	N.V.
TF/FP-115B-L	2.90	1.15	0.38
TF/FP-130B-L	3.30	1.50	0.38
TF/FP-190B-L	4.80	1.65	0.38
TF/FP-240B-L	6.10	3.80	0.50
TF/FP-350B-L	8.90	5.40	0.65
TF/FP-480B-L	12.20	8.00	0.80
TF/FP-700B-L	17.80	12.70	1.00
TF/FP-990B-L	25.40	17.80	1.15

*other dimensions on request

Packaging: 1.22m lengths. Special sizes on request.
Processing note: Care for clean and accurate cutting edges. Start shrinkage on the end. Pre-heat metal body.

FITCO® = trademark of GREMCO
 All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

PTFE heat shrink tubing with melting FEP core

FITCOTUBE® TF/FP-B

Properties	Testing	PTFE-Value	FEP-Value
Mechanical			
Density	ISO 1183	2,14-2,19g/cm ³	2,12-2,17g/cm ³
Tensile strength	ISO 527	≥29N/mm ²	≥19N/mm ²
Elongation at break	ISO 527	≥200%	≥250%
Shore hardness	ISO 868	D 55-72	D 55-60
Thermal			
Melting temperature	ISO 12086	327°C	253-282°C
Longitudinal shrinkage	--	±10%	±10%
Operating temperature	--	-200°C bis +260°C	-190°C bis +205°C
Electrical			
Dielectric constant (100Hz)	IEC 60250	<2,1	<2,1
Dielectric loss factor	--	0,5-0,7*10 ⁻⁴	0,5-0,7*10 ⁻⁴
Volume resistivity	IEC 60093	>10 ¹⁶ Ω	>10 ¹⁶ Ω