

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT-WB-U

FITCOTUBE® FT-WB-U is a hot-melt adhesive lined, heat-shrink tubing designed to provide excellent insulation, moisture protection and sealing of electrical splices. The product is particularly suited for encapsulation of wire to metal splices within the automotive sector protecting wires from corrosion.

FITCOTUBE® FT-WB-U will also provide superior strain relief, mechanical protection against abrasion, cut through and flexing.

Operating temperature: -40°C to +130°C

Min. shrink temperature: +100°C

Min. full shrink temperature: +135°C

Shrink ratio: 4:1

Standard colors: Black



Dimensions:

Description	As supplied		After shrinkage	
	ID min. (mm)	WT nom. (mm)	ID max. (mm)	WT nom.** (mm)
FT-WB-U 400	4.0	0.45	1.0	1.0
FT-WB-U 570	5.7	0.45	1.3	1.2
FT-WB-U 740	7.4	0.55	1.7	1.6
FT-WB-U 900	9.0	0.65	2.3	1.8
FT-WB-U 1100	11.0	0.65	2.4	2.0
FT-WB-U 1200	12.0	0.65	2.5	2.2
FT-WB-U 1400	14.0	0.80	3.0	2.2
FT-WB-U 1830	18.3	0.75	4.4	2.4
FT-WB-U 2600	26.0	0.65	6.5	2.4

**Wall thickness will be less if tubing recovery is restricted during shrinkage.

Tolerance from nominal, ≤30% eccentricity.

Packaging: Basically cut to length according to customer requirements, otherwise 1.2 meter rods.

Processing note: Care for clean and straight cutting edges. Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272.63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de •

PDS No.: 20240424093545

Version: UWM0424-2

Print Date: 12. Mai. 2025

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT-WB-U

Attributes	Testing	Requirements
Mechanical		
Tensile strength	ASTM D 2671	≥10.3 MPa
Breakdown elongation	ASTM D 2671	≥250 %
Longitudinal change	ASTM D 2671	-7% to +3%
Secant Modulus at 2 % (recovered)	ASTM D 2671	≥137 MPa
Dynamic cut through	ASTM D 3032	≥13.6 kg
Volume resistivity	ASTM D 2671	≥1.0×10 ¹⁴ Ω*cm
Thermal		
Heat shock (225°C x 4 hrs)	ASTM D 2671	No dripping, flowing or cracking of outer jacket
Flammability	ISO 6722	Self-extinguishing within 60s

FITCO® = trademark of GREMCO
All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.