

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT300

Flexible, self-extinguishing heat shrink tubing made of irradiated cross-linked polyolefin and with high shrink ratio..

Insulation, protection and mechanical relief of wires, cables, harnesses and connectors with a large difference in diameter.

Wide variety of applications. High shrink ratio reduces number of sizes.

Operating temperature: - 55°C to + 135°C

Min. Shrink temperature: + 90°C

Shrink ratio: 3 : 1

Standard colors: Black, Blue, Red, White, Yellow
Special colors on request

Specification/Approvals: UL 224 125°C 600V VW-1 (File No. UL E191514), Mil Spec. M23053/5



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)
FT300-1,5/0,5	1.50	0.50	0.50
FT300-3/1	3.00	1.00	0.60
FT300-4,8/1,6	4.80	1.60	0.65
FT300-6/2	6.00	2.00	0.70
FT300-9/3	9.00	3.00	0.80
FT300-12/4	12.00	4.00	0.85
FT300-18/6	18.00	6.00	1.00
FT300-24/8	24.00	8.00	1.20
FT300-40/13	40.00	13.00	1.25

Packaging: On spools. Cut lengths or printed tubing on request.
Special sizes on request.

Processing note: Care for clean and straight cutting edges. Start shrinkage on the end.
Pre-heat metal body.

Polyolefin Heat-Shrink Tubing

FITCOTUBE® FT300

Properties	Test Method	Requirements	Typical Value
Mechanical			
Tensile strength	ASTM D 638	Min. 10.4 MPa	≥ 12 MPa
Elongation	ASTM D 638	min. 200%	440%
After thermal ageing (158°C / 168h): Tensile strength Elongation	UL 224	7.3MPa >100%	12.5MPa 450%
Thermal			
Low temperature flexibility (1h x -30°C)	UL 224	No cracking	Pass
Heat shock (4h x 250°C)	SAE-AS23053	No cracking, flowing or dripping	Pass
Flammability	UL 224	VW-1	Pass
Electrical			
Dielectric withstand	AC 2.5kV x 60s	no breakdown	Pass
Dielectric breakdown	min. AC 2.5kV		24.8kV
Volume resistance	-	Min. 10 ¹⁴ Ωxcm	5.8 x 10 ¹⁴ Ωxcm
After thermal ageing (158°C / 168h) Dielectric withstand Dielectric breakdown	UL 224	2,5kV AC x 60s min. 2.5kV AC and ≥50%	Pass Pass
Chemical			
Copper corrosion (168h x 158°C)	95%humidity, 23°C / 24h	No corrosion	Pass
Copper stability (168h x 158°C)	95%humidity, 23°C / 24h	Elongation: Min. 100%	Pass