

Braid hot shrinking tube

FITCOFLEX®-HS

Braid hot shrinking tube with high shrinking rate

Application:

Abrasion protection for pipes, tubing cable bundle and tubesystems. Universal application for large number of different diameter ranges due to its high extension rate. Reduces storage!

Operating temperature:

-40°C up to +125°C (3.000h) / -40°C up to 150°C (1.000h)

Standard color: black

Descriptions:	Recommended Application [mm]
FITCOFLEX-HS 8/4	4 – 6
FITCOFLEX-HS 12/6	6 – 9
FITCOFLEX-HS 20/10	10 – 15
FITCOFLEX-HS 25/12,5	12,5 – 18
FITCOFLEX-HS 30/15	15 – 22
FITCOFLEX-HS 34/17	17 – 25
FITCOFLEX-HS 40/20	20 – 30
FITCOFLEX-HS 50/25	25 – 37
FITCOFLEX-HS 55/27,5	27,5 – 43
FITCOFLEX-HS 60/30	30 - 45

Special sizes on request

Features:

- Material: Polyester Multifilaments & shrinking polyolefine monofilaments
- Processing temp. 180°C up to 230°C
- Very good fluid resistance
- Extreme abrasion resistance
- Low weight, high flexibility
- Free of halogenous

Braid hot shrinking tube

FITCOFLEX®-HS

Packaging options:
On spools, Laser cut lengths

Features:

	Test Method	Result
Abrasion resistance	LV 312-3 (ISO 6722) PSA 9645870999E GME 8618 TL 52668	≥ 5.000 cycles (class E) 144.000 cycles (Classification 5) 500 strokes 144.000 cycles
Flammability	FMVSS 302 (DIN 75200)	Flammability speed ≤100mm/min (category C)
Shrinking	ISO 6722	≤ 10%
Impact performance	PSA D421245 LV 312-3	No damages (C/200/50/-30°C) No damages (700/1200g with -40°C)
Hydrolysis resistance	GME 00053	Fulfilled
Thermal ageing	GMW 14327 / ISO 188 Methode B GME 00052 Fiat 9.91220	Fulfilled (240 h / 125°C) Fulfilled (24 h / 175°C) Fulfilled (240 h / 150°C)
Fogging	VW 50180	Fulfilled (≤ 2mg)
Emission	VW 50180	Fulfilled (≤ 50µg C/G)
Ozone resistance	PSA D411100	Fulfilled