

Polyolefin heat-shrink tubing

FITCOTUBE® FT010

Halogen-free, flame-resistant heat-shrink tubing with flat surface. Use as cable labelling and wire sheath in military technology, vehicles for mass transport and public buildings. High flexibility at low temperatures.

Operating temperature: - 40°C to + 105°C

Shrink temperature: + 120° C

Shrink ratio: 2 : 1

Standard colors: Black

Approvals: ASTM, BS 6853, BSS 7239 Boeing Specification Support Standard, Japanese Standard for railway vehicle material, LUL: London Underground Limited Eng. Stand. E 1042. A6, SAE-AMS-DTL-23053, EN45545-2, IEC 60684-3-216



Standard dimensions:

Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after full recovery (max.)	after full recovery (nom.)
FT010-160	1.60	0.80	0.70
FT010-240	2.40	1.20	0.70
FT010-320	3.20	1.60	0.70
FT010-480	4.80	2.40	0.85
FT010-640	6.40	3.20	0.90
FT010-950	9.50	4.80	1.00
FT010-1270	12.70	6.40	1.20
FT010-1900	19.10	9.50	1.40
FT010-2540	25.40	12.70	1.80
FT010-3800	38.10	19.10	1.80
FT010-5100	50.80	25.40	2.20

Packaging: On Spools.
Cut and printed lengths on request.

Processing note: Care for clean and accurate cutting edge.
Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-55 · info@gremco.de · www.gremco.de

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Gremco make no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Gremco's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will Gremco be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Polyolefin heat-shrink tubing

FITCOTUBE® FT010

Attributes	Testing	Value
Mechanical		
Tensile strength	ASTM D 638	pass (min. 10.4 MPa)
Ultimate Elongation	ASTM D 638	pass (min. 200 %)
Longitudinal Change	IEC 60684-3-216	pass (5 to -10%)
Elastic modulus	ASTM D 882	pass (max. 173 MPa)
Thermal		
Low temperature flexibility (-40°C x 4 h)	SAE-AMS-DTL-23053	no cracking
Elongation after long-term ageing (136°C x 168 h)	ASTM D 638	pass
Short-term ageing (225°C x 4 h)	SAE-AMS-DTL-23053	pass
Fire behavior	LUL: London Underground	self-extinguishing
Electrical		
Dielectric strength	ASTM D 876	≥ 19.7 KV/mm
Volume resistivity	ASTM D 876	≥ 6 x 10 ¹³ Ω/cm
Chemical		
Halogen content	NFX-70-100 BS 6853	zero
Water absorption	ASTM D 570	≤ 1.0
Copper Corrosion	SAE-AMS-DTL-23053	no corrosion
Safety-relevant		
Oxygen index	EN 45545-2	≥ 37
Smoke density	EN 45545-2	< 150:R22 / HL3
Toxic gas evolution	BSS 7293	pass
Toxic smoke development	EN 45545-2	< 0.75: R22 7 HL3