

PVDF Heat-Shrink Tubing

FITCOTUBE[®] FT190

Semi-rigid, abrasion resistant, flame-resistant high temperature-PVDF-heat shrink tubing with reliable insulation and excellent mechanical protection of wires and components in high temperature environment. Protection of soldering and crimp connections. High chemical stability.

- Operating temperature:** - 55°C to + 190°C, short time up to + 300°C
- Shrink temperature:** + 175° C
- Shrink ratio:** 2: 1
- Standard colors:** Transparent
- Specification:** UL File E191539, CSA (233954)



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)
FT190-120	1.20	0.60	0.25
FT190-160	1.60	0.80	0.25
FT190-240	2.40	1.20	0.27
FT190-270*	2.70	1.20	0.27
FT190-320	3.20	1.60	0.27
FT190-350*	3.50	1.60	0.50
FT190-480	4.80	2.40	0.27
FT190-640	6.40	3.20	0.33
FT190-950	9.50	4.80	0.33
FT190-1270	12.70	6.40	0.33
FT190-1910	19.10	9.50	0.43
FT190-2540	25.40	12.70	0.48
FT190-2810	28.10	19.10	0.51
FT190-5180	50.80	25.40	0.51

*Spezial Sizes on Request

- Packaging:** Cut-Lengths of 1200 mm.
Special sizes on request.
- Processing note:** Care for clean and accurate cutting edge. Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-44 · info@gremco.de · www.gremco.de • Version: 1908

FITCO[®] = trademark of GREMCO
All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GREMCO make no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. GREMCO's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GREMCO be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

PVDF Heat-Shrink Tubing

FITCOTUBE[®] FT190

Attributes	Testing	Requirements	Value
Mechanical			
Tensile strength	ASTM D 412	min. 34.5 MPa	≥ 40 MPa
Ultimate elongation	ASTM D 412	min. 150 %	≥ 350 %
Longitudinal change	SAE-AMS-DTL-23053	± 10 %	- 7 %
Specific Gravity	ASTM D 792	max. 1.8	1,76
Secant Modulus	ASTM D 882	min. 828 MPa	≥ 840 Mpa
Thermal			
Low temperature flexibility (-55 °C x 4h)	SAE-AMS-DTL-23053	no cracking	pass
Elongation after long-term ageing (250°C x 168h)	ASTM D 638	min. 50 %	≥ 200 %
Short term ageing (300°C x 4h)	SAE-AMS-DTL-23053	no cracking, flowing or dripping	pass
Fire behavior	UL 224/CSA	VW-1	pass/self-extinguishing
Electrical			
Dielectric Strength (> ½ inch)	SAE-AMS-DTL-23053	min. 23.6 kV/mm	≥ 30 kV/mm
Dielectric Strength (≤ ½ inch)	SAE-AMS-DTL-23053	min. 31.5 kV/mm	≥ 35 kV/mm
Volume Resistivity	ASTM D 876	min. 10 ¹³ Ω/cm	≥ 10 ¹⁵ Ω/cm
Dielectric Voltage Withstand (2.5 kV x 60 s)	SAE-AMS-DTL-23053	no breakdown	pass
Chemical			
Copper Corrosion (160°C x 16 h)	SAE-AMS-DTL-23053	no corrosion	pass
Water Absorption	ASTM D 570	max. 0.5 %	≤ 0,2 %
Fluid Resistance	SAE-AMS-DTL-23053	-	-
Dielectric Strength (23 °C x 24 h)	-	19.7 kV/mm	pass
Fungus Resistance	SAE-AMS-DTL-23053	ASTM G 21	pass