

Polyolefin heat-shrink tubing

FITCOTUBE® FT555

Halogen free, high performance, flexible, cross-linked polyolefin heat shrink tubing. Reliable insulation, mechanical protection of harnesses, variety of colors for marking.

Operating temperature:	- 70°C to +135°C short time up to +200°C
Shrink temperature:	+ 90° C
Shrink ratio:	2 : 1
Standard colors:	Black



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)
FT555-120	1,20	0,60	0,31
FT555-160	1,60	0,80	0,33
FT555-240	2,40	1,20	0,36
FT555-320	3,20	1,60	0,39
FT555-480	4,80	2,40	0,42
FT555-640	6,40	3,20	0,45
FT555-950	9,50	4,80	0,48
FT555-1270	12,70	6,40	0,52
FT555-1900	19,00	9,50	0,58
FT555-2540	25,40	12,70	0,67
FT555-3200	32,00	16,00	0,76
FT555-3800	38,00	19,00	0,76
FT555-5100	51,00	25,40	0,85
FT555-7600	76,00	38,00	0,95
FT555-10200	102,00	51,00	1,05

Packaging: On spools, cut lengths or printed tubing on request.
Special sizes on request.

Polyolefin heat-shrink tubing

FITCOTUBE® FT555

Attributes	Testing	Value
Mechanical		
Tensile strength	ASTM D 638	min 10,4 MPa (pass)
Ultimate elongation	ASTM D 638	≥ 400 %
Longitudinal change	SAE-AMS-DTL-23053	- 5 %
Specific Gravity	ASTM D 792	nom. 1,1 (pass)
Secant Modulus	ASTDM D 882	≤ 100 MPa
Thermal		
Heat Shock (225°C x 4h)	UL 224	No cracking, flowing or dripping
Cold bend (-70°C x 4h)	UL 224	No cracking
Elongation after heat ageing (136°C x 168h)	SAE-AMS-DTL-23053	≥ 170%
Tensile Strength after heat ageing (136°C x 168h)	SAE-AMS-DTL-23053	min 7,3 MPa (pass)
Flammability	FMVSS 302	Pass
Electrical		
Dielectric strength	ASTM D 876	> 23KV/mm
Dielectric Voltage Withstand (2,5kV x 60s)	UL 224	Pass
Volume Resistivity	ASTM D 257	10 ¹⁴ Ω/cm
Chemical		
Copper Corrosion (175°C x 16h)	UL 224	Pass
Fluid Resistance (23°C x 24h)*	SAE-AMS-DTL-23053	Tensile Strength: min 10,4 MPa (pass) Elongation: min 200% (pass)

* Tested fluids: Gasoline, Simulated Windshield cleaner, Brake Fluid, Anti-freezing fluid, Battery fluid, Engine oil, Torque conversion oil