

Polyolefin heat-shrink tubing

FITCOTUBE® FT800E-HT

Flexible, high-temperature resistance heat-shrink tubing coated with adhesives. Suitable for moisture- and waterproof encapsulation of wires, cables, pinching- and plug connections as well as other electrical and mechanical components.

Operating temperature: - 55°C to + 125°C, short term up to + 250°C

Shrink temperature: > 100° C

Shrink ratio: 3 : 1 and 4 : 1

Standard colors: Black



Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)
3 : 1			
FT800E-HT-3/1	3.00	1.00	1.00
FT800E-HT-4.8/1.5	4.80	1.50	1.00
FT800E-HT-6/2	6.00	2.00	1.10
FT800E-HT-9/3	9.00	3.00	1.30
FT800E-HT-12/4	12.00	4.00	1.70
FT800E-HT-18/6	18.00	6.00	2.00
FT800E-HT-24/8	24.00	8.00	2.50
FT800E-HT-39/13	39.00	13.00	2.50
4 : 1			
FT800E-HT-4/1	4.00	1.00	1.02
FT800E-HT-8/2	8.00	2.00	1.02
FT800E-HT-12/3	12.00	3.00	1.30
FT800E-HT-16/4	16.00	4.00	1.78
FT800E-HT-24/6	24.00	6.00	2.10
FT800E-HT-32/8	32.00	8.00	2.50
FT800E-HT-52/13	52.00	13.00	2.50

Packaging: On spools or 1.2 meter lengths. Special sizes and cut lengths on request.

Processing note: Care for clean and straight cutting edges. Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272.63-0 · F +49.821.272.63-55 · info@gremco.de · www.gremco.de

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Gremco make no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Gremco's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will Gremco be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

Polyolefin heat-shrink tubing

FITCOTUBE® FT800E-HT

Attributes	Testing	Value
Mechanical		
Tensile strength	ASTM D 638	11 N/mm ²
Ultimate elongation	ASTM D 638	300 %
Longitudinal change	ASTM D 2671	- 15 % to + 1 %
Specific gravity	ASTM D 792	1.45
Thermal		
Low temperature flexibility (- 55°C)	ASTM D 2671 C	no cracking
Short-term aging (250° C x 4h)	ASTM D 2671	no cracking, flowing or dripping
Flammability	ASTM D 2671 (B)	pass
Electrical		
Dielectric strength	ASTM D 2671	15 kV/mm
Specific volume resistivity	ASTM D 257	10 ¹⁴ Ω/cm
Chemical		
Water absorption	ASTM D 570	≤ 0.5 %