

PTFE- heat-shrink tubing

FITCOTUBE® TF/TFR

Heat-shrink PTFE tubing with extreme chemical and thermal stability. Electrical insulation of components, wires and harnesses in high temperature environments.

Operating temperature:	- 67° C to + 250° C, short time up to + 400° C
Shrink temperature:	+ 327° C
Shrink ratio:	1.5 – 3.5 : 1
Standard color:	Clear
Authorisations:	MIL-I-23053/12, AMS 3584 & 3585

Description	Inner diameter (mm)		Wall thickness (mm)
	as supplied (min.)	after shrinkage (max.)	after shrinkage (nom.)
TF-30	0.86	0.38	0.23
TF-28	0.97	0.46	0.23
TF-26	1.17	0.56	0.23
TF-24	1.27	0.64	0.25
TF-22	1.40	0.80	0.25
TF-20	1.52	0.97	0.30
TF-18	1.93	1.17	0.30
TF-16	2.35	1.45	0.30
TF-14	3.05	1.82	0.30
TF-12	3.81	2.26	0.30
TF-10	4.85	2.80	0.30
TF-8	6.10	3.55	0.38
TF-6	7.67	4.40	0.38
TF-4	9.40	5.45	0.38
TF-2	10.90	6.90	0.38
TF-0	11.95	8.56	0.38
TFR 5/64	1.98	0.64	0.22
TFR 1/8	3.18	0.94	0.25
TFR 1/4	6.35	1.60	0.30
TFR 3/8	9.52	2.44	0.30
TFR 1/2	12.70	3.66	0.38
TFR 5/8	15.88	4.52	0.38
TFR 3/4	19.05	5.70	0.38
TFR 1	25.40	7.06	0.38
TFR 1 1/4	31.75	8.82	0.38
TFR 1 1/2	38.10	10.20	0.38

Packaging: 1.2-meter lengths. On spools on request. Thin-walled dimensions on request.

Processing note: Care for clean and accurate cutting edge. Start shrinkage on the end.
Pre-heat metal body.

GREMCO GmbH · Sterzinger Str. 6 · D-86165 Augsburg · T +49.821.272 63-0 · F +49.821.272.63-55 · info@gremco.de · www.gremco.de

FITCO® = trademark of GREMCO

All of the above information is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. GreMco make no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. GreMco's only obligations are those in the Standard Terms and Conditions of Sale for this product, and in no case will GreMco be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use or misuse of the product.

PTFE- heat-shrink tubing

FITCOTUBE[®] TF/ TFR

Attributes	Testing	Value
Mechanical		
Tensile strength	ISO 527	29 - 39 N/mm ²
Ultimate elongation	ISO 527	200 - 500 %
Water absorption		< 0.05
Thermal		
Fire behavior		incombustible
Electrical		
Dielectric strength	IEC 60243-2	> 40kV/mm